



TYPICAL PROPERTIES	TEST STANDARD	UNITS S.I.	6755	6765	6775
DENSITY	ISO 1183	kg/m ³	915	915	914
HARDNESS (5 SEC DELAY) Injection molded sample	ISO 868	Shore A or D	61A	70A	78A
TENSILE PROPERTIES <i>Cross flow direction</i>					
Tensile strength at break	ISO 37	MPa	4.3	5.5	6.6
Modulus at 100% elongation		MPa	1.6	2.1	2.6
Elongation at break		%	630	660	690
TEAR STRENGTH <i>Cross flow direction</i>					
Unnicked angle	ISO 34B	kN/m	22	26	32
COMPRESSION SET 24 hrs @ 70°C	ISO 815	%	34	36	40
APPARENT SHEAR VISCOSITY @ 206 1/s, 200°C	ISO 11443	Pa.s	216	230	227

FEATURES

- Lighter, natural color providing improved colorability for custom colors
- High flow properties ensure that even complex shapes with thin walls are molded with ease
- UV stable
- Low fogging
- Non-hygroscopic nature; pre-drying is not necessary
- Resistant to hydrocarbons and aqueous liquids
- Good thermal stability
- Available in 55 to 75 Shore A, in natural only

TRANSPORTATION SEGMENTS

- Interior

Revised January 2017

AMERICAS

505 Central Avenue
Pawtucket, RI 02861 USA
401-725-8000 | 800-556-3862

EUROPE

Mijnweg 1
6167AC Geleen, Netherlands
31(0) 46 7020950

ASIA

41 Shipyard Road
Singapore 028134
(011) 65-6265-2544



tpe@teknorapex.com | www.teknorapex.com

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchaser assumes all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described. For detailed Product Stewardship information, please contact us. Any product of Teknor Apex, including product names, shall not be used or tested in any medical or food contact application without the prior written acknowledgment of Teknor Apex as to the intended use. Please note that some products may not be available in one or more countries. Data contained in this bulletin supercedes all previous versions. © Copyright 2015 Teknor Apex Company. All rights reserved.