



TYPICAL PROPERTIES	TEST STANDARD	UNITS S.I.	ME-2555B	ME-2565B	ME-2570B
<b>DENSITY</b>	ISO 1183	kg/m <sup>3</sup>	1110	1110	1110
<b>HARDNESS (5 SEC DELAY)</b> Injection molded sample	ISO 868	Shore A or D	55A	61A	71A
<b>TENSILE PROPERTIES</b>					
<b>Flow direction</b>					
Tensile strength at break	ISO 37	MPa	5.9	6.3	6.5
Modulus at 100% elongation		MPa	1.7	1.9	2.1
Elongation at break		%	780	770	800
<b>Cross flow direction</b>					
Tensile strength at break	ISO 37	MPa	6.5	6.5	5.9
Modulus at 100% elongation		MPa	1.4	1.6	2.3
Elongation at break		%	850	820	730
<b>TEAR STRENGTH</b>					
<b>Cross flow direction</b>	ISO 34B				
Unnicked angle		kN/m	23	25	28
<b>COMPRESSION SET</b>					
22 hrs @ 23°C	ISO 815	%	19	21	22
22 hrs @ 70°C		%	39	42	46
70 hrs @ 90°C		%	71	72	76
<b>HOT AIR AGING</b>					
<b>Cross flow direction</b>					
<b>168 hrs @ 125°C</b>					
Change in hardness	ISO 188	pts	4	4	5
Change in tensile strength at break		%	9	8	12
Change in modulus at 100% elongation		%	-	-	-
Change in elongation at break		%	11	11	12
<b>1000 hrs @ 110°C</b>					
Change in hardness		pts	1	3	3
Change in tensile strength at break	ISO 188	%	6	3	-11
Change in modulus at 100% elongation		%	-	-	-
Change in elongation at break		%	2	4	2
<b>APPARENT SHEAR VISCOSITY</b> @ 206 1/s, 200°C	ISO 11443 Capillary	Pa.s	127	123	123

**FEATURES**

- High flow properties for excellent moldability
- Class A surface appearance
- Adhesion to glass with use of primer
- Excellent UV resistance
- Good elastic performance
- Available from 55 to 70 Shore A, in black only

**TRANSPORTATION SEGMENTS**

- Sealing Systems
- Exterior
- Under the Hood

Revised April 2018

**AMERICAS**

505 Central Avenue  
Pawtucket, RI 02861 USA  
401-725-8000 | 800-556-3862

**EUROPE**

Mijnweg 1  
6167AC Geleen, Netherlands  
31(0) 46 7020950

**ASIA**

41 Shipyard Road  
Singapore 028134  
(011) 65-6265-2544



tpe@teknorapex.com | www.teknorapex.com

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchaser assumes all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described. For detailed Product Stewardship information, please contact us. Any product of Teknor Apex, including product names, shall not be used or tested in any medical or food contact application without the prior written acknowledgment of Teknor Apex as to the intended use. Please note that some products may not be available in one or more countries. Data contained in this bulletin supercedes all previous versions. © Copyright 2018 Teknor Apex Company. All rights reserved.